

# 3M™ Scotchkote™

## Liquid Epoxy Coating 323

### Data Sheet


#### Product Description

3M™ Scotchkote™ Liquid Epoxy Coating 323 is a two-part system designed to help protect steel pipe and other metal surfaces from the harsh affects of corrosion.

#### Intended Uses

- As a patch material.
- As a girthweld coating.
- As an internal lining
- As a stand alone coating for pipe rehabilitation.

#### Product Features

- No solvents needed. VOC as mixed 12 g/L.
- High build, up to 45 mils/1150 microns in one application.
- Applicable by cartridge, brush, roller, HSS or plural component spray.
- Excellent adhesion.
- 100% solids.
- Can be applied to a substrate as cold as 41°F/5°C.
- Meets the requirements of AWWA C210.
- Resistant to damage from acids and bases in pH range 2-14.
- Resistant to hydrocarbons such as crude oil, motor oils and gasoline.
- Certified to ANSI/NSF Standard 61, Drinking Water System Components. 

#### General Application Steps

**For use as a joint coating, a refurbishing coating or as a pipe coating:**

1. Remove oil, grease and loosely adhering deposits.
2. Abrasive blast clean the surface to NACE No. 2/SSPC-SP10, ISO 8501:1, Grade SA 2 1/2 near-white metal.
3. Ensure the abraded surface is cleaned of abrading debris with the use of an air blast or a clean lint free cloth then verify anchor profile is 1.5 - 4 mils.
4. Within four hours of blasting as per the above cleaning process and with the metal above 41°F/5°C and a minimum of 5°F/3°C above the dew point, apply Scotchkote 323 at recommended film thickness. Allow to cure.
5. Repair all defects using Scotchkote 323.

**For use as a repair material in the field where scratches or other holidays may have occurred.**

1. Remove oil, grease and loosely adhering deposits.
2. Abrade the FBE surface with medium grit sandpaper (approx 80 grit). Powered rotary sanders and sweep blasting are also acceptable means of performing this task as well. Ensure that the surrounding FBE is roughened for 10 mm on all sides of the holiday.
3. Ensure the abraded surface is cleaned of abrading debris with the use of an air blast or a clean lint free cloth then verify anchor profile is 1.5 - 4 mils.
4. With the metal above 41°F/5°C and a minimum of 5°F/3°C above the dew point, apply Scotchkote 323 at recommended film thickness.

#### 3M™ Scotchkote™ 323 Coverage per kit size (Assumes no waste)

Kit	lbs of material		Coverage in square feet @ mils		
	Total	25 mils	28 mils	30 mils	
50 ml	0.15	0.85	0.76	0.71	
450 ml	1.34	7.63	6.81	6.36	
Quart	2.10	11.90	10.60	9.90	
Gallon	8.70	47.70	42.60	39.70	
5-gal x 3	152.10	865.80	773.00	721.50	
55-gal drum x 3	1,690.40	9,621.80	8,590.90	8,018.10	



## Properties

Property	Test Description	Value
Color		Blue-Green
Mix Ratio		2A : 1B by volume 70.8% : 29.2% by weight
Viscosity in cps @		
• Brush Grade 72°F/22°C		Part A: 154,000 Part B: 6,000
• Spray Grade 72°F/22°C		Part A: 90,000 Part B: 19,000
Shelf Life (unopened container)		24 months
Specific Gravity		1.35 mixed
Coverage		142 ft <sup>2</sup> /(lb/mil) (0.74m <sup>2</sup> /(kg/mm))
Recommended Coating Thickness		25-60 mils (625-1500 microns)
Shyodu Gel Time (approximate pot life)	200 gm mass	75°F / 24°C      20 Min 104°F / 40°C      11 min
Dry to Touch Time	ASTM D1640 clause 7.5.2	41°F / 5°C      7 hrs 75°F / 24°C      1 hr 45 Min 122°F / 50°C      26 min
Approximate Back Fill Time (For additional information see chart below)	ASTM D1640 clause 7.7.1	41°F / 5°C      8 hrs 75°F / 24°C      2 hr 39 min 122°F / 50°C      39 min

## Typical Test Properties

Property	Test Description	Typical Value
Cathodic Disbondment (steel grit blasted plates laboratory applied; results may vary depending on blast media)	CSA Z245.20-06 clause 12.8	149°F / 65°C, 3.5V, 24 hrs      4.9 mmr 149°F / 65°C, 1.5V, 48 hrs      5.5 mmr 149°F / 65°C, 1.5V, 28 days      7.5 mmr 176°F / 80°C, 1.5V, 14 days      6.4 mmr 176°F / 80°C, 1.5V, 28 days      6.6 mmr
Hot Water Soak Adhesion of Coating	CSA Z245.20-06 clause 12.14	203°F / 95°C      24 hrs      Rating 1 167°F / 75°C      48 hrs      Rating 1 167°F / 75°C      28 days      Rating 1
Dry Adhesion (Pull off strength)	ASTM D 4541-02 Type 4	4000 psi
Flexibility	CSA Z245.20-06 clause 12.11	68°F / 20°C      1.0/PD 32°F / 0°C      1.0/PD
Abrasion Resistance	ASTM D4060-06 CS-17 wheels 1000 g load 5000 cycles wheels resurfaced every 500 cycles	0.325 g loss
Impact Strength	ASTM G14	> 1.5j
Hardness	ASTM D-22 40-97	Shor D 85 ± 1

## Handling and Safety Precautions

Read all Health Hazard, Precautionary and First Aid, Material Safety Data Sheet, and/or product label prior to handling or use.

## Ordering Information/Customer Service

For ordering technical or product information, or a copy of the Material Safety Data Sheet, call:

Phone: **800/878-8837**

Fax: **925/427-6202**

## Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

## Warranty; Limited Remedy; Limited Liability.

Because conditions of product use are outside of our control and vary widely, the following is made in lieu of all express or implied warranties: this product will conform to 3M's published product specifications and be free from defects in material and manufacture on the date of your purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective upon your receipt, your exclusive remedy shall be, at 3M's option, to replace the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.**



Corrosion Protection Products Division



### DISTRIBUTED BY:

2201 Harbor St, Unit C  
Pittsburg, CA 94565  
Tel: 800.878.8837

302 South 700 West  
Pleasant Grove, UT 84062  
Tel: 801.785.1546

Please recycle. Printed in USA.  
© 3M 2011. All rights reserved.  
80-6111-8345-2-Rev Q