



Casing End-Seal Application Procedures

1. With a wire brush, clean the last 12" of the casing pipe ends and the first 12" of the carrier pipe to remove loose rust, coating, and dirt. Dry off all surfaces.
2. Brush Seal-Wrap™ Primer onto the cleaned areas of the carrier and casing to be covered with Seal-Wrap™. Let dry until tacky.
3. Place one layer of Double-Faced Adhesive at the edge of the casing and one layer approximately 4" from the end of the casing on the carrier pipe. Remove release paper from the Double-Faced Adhesive. This is the area where the banding will be applied.
4. Measure around outside circumference of the casing to determine length for a single wrap of Seal-Wrap, then add 6" to ensure that Seal-Wrap is cut long enough to allow for a 6" overlap. Apply one wrap of Seal-Wrap around the carrier and casing end. One edge of the Seal-Wrap should be aligned with the farthest edge of the Double-Faced Adhesive on the casing. Remove release paper as you apply the Seal-Wrap.
5. Band securely in place, using one band and two buckles on both casing and carrier in the middle of the Double-Faced Adhesive. Use the banding tool to tighten bands until flush with the surface of the Seal-Wrap, then tighten both buckles with the supplied hexagonal wrench.
6. Cover buckles with small squares (approx. 6" square) of Double-Faced Adhesive to prevent cutting of next layer. Remove release paper from Double-Faced Adhesive.
7. Apply a continuous double wrap of Seal-Wrap directly over the first wrap, making sure to start the second wrap in a different position than the first. Remove release paper as you apply the Seal-Wrap. (To determine the length of Seal-Wrap, double the casing circumference, then add 6" for overlap.)
8. Apply one wrap of Double-Faced Adhesive centered over the edge of the casing end and one wrap centered over the edge where the Seal-Wrap meets the carrier pipe. Do not remove release paper from the Double-Faced Adhesive.
9. Place two bands on the carrier pipe on either side of the first band. The band closest to the end of the casing should be over the Double-Faced Adhesive applied in Step 8.
10. Place two bands on the casing pipe on either side of the first band. The band closest to the end of the casing should be over the Double-Faced Adhesive applied in Step 8.
11. Tighten all bands into place so they seat securely into the Double-Faced Adhesive and Seal-Wrap.
12. Let the seals cure overnight.
13. Apply up to 2 psi into top vent, then check for a strong airflow escaping out the lower end vent. This confirms there are no restrictions between vents.
14. Close off the lower end vent, pressure casing up to 2 psi, and monitor for 15 minutes. If air pressure holds, the test is complete and the casing is prepared. It is highly recommended to backfill before testing above 2 psi.
15. If casing is to be filled with wax, it is highly recommended/critical that the ends of the casing are backfilled. The backfill will help support the seals, and help stop any minor leaks.



DISTRIBUTED BY:

PROTECTION
Pipeline Products, Protective Coatings & Cathodic Protection

2201 Harbor St, Unit C
Pittsburg, CA 94565
Tel: 800.878.8837

ENGINEERING

302 South 700 West
Pleasant Grove, UT 84062
Tel: 801.785.1546